

Rocky SL 10

Description

ROCKY SL 10 is a fine powder composed of cement, selected aggregates, additives and special synthetic resins. When mixed with water it forms a very fluid and flowing mixture, perfectly leveling, with easy application, and good adhesion to the support.

Use

ROCKY SL 10 is used for horizontal surface leveling with thickness from 3 to 10 mm.

It can be applied internally as screed on concrete for existing floors of ceramics, marble, etc. before laying the ceramic tiles or other floor types.

Advantages

- Can be used internally
- Flowable consistency for self-leveling application
- Minimal shrinkage with outstanding resistance to cracking
- Excellent bonding strength
- Economical and easy to use

Technical Properties

Appearance	Grey Powder
Density at 25°C	2.0 kg/L
Working time of mixture at 25°C	30 minutes
Pull off bond strength	1.0 N / mm ²
BRE Screed test (BS 8204 Pt.1)	0.6mm
VOC	2.0 g/L
Compressive Strength at 28 days (BS EN 13892)	> 30 N/mm ²
Flexural Strength at 28 days (BS EN 13892)	> 8 N/mm ²
Tensile Strength (BS EN 13892)	1 N/mm ²
Shrinkage Test (BS EN 13872)	1 mm/m
Initial setting time at 25°C	3 ½ hours
Final setting time at 25°C	5 hours
Time to wait before tiles laying	48 hours
Service Temperature	+5°C to +80°C

Rocky SL 10

Priming

The substrate must be treated with ROCKY SR 200, a synthetic resin high penetrating primer.

ROCKY SR 200 should be applied by brush or roller on to the cleaned surface area (particularly hidden surfaces) at a rate of 5-6m²/Liter.

The primer should be left to achieve a tack-free condition before applying the topcoat. A second coat of primer may be required if the substrate is excessively porous.

Mixing

Pour into a container with 6.0 Liters of water the 25 Kg bag of ROCKY SL 10. Mix with a low-speed electric drill fitted with a suitable paddle for 2 minutes scraping sides and bottom of the can, until a uniform, lump free consistency mix is achieved. Allow the mix to stand for 3 minutes and then remix again for 30 seconds.

Mix a quantity of product that can be applied within 30 minutes only. Do not remix with water if the mixture had already begun to set

Application

Pour the mixed product into the surface and spread to the desired thickness using flooring rake and a spike roller.

Protect the floor after leveling the mix from direct sunlight, high winds or rain

ROCKY SL 10 can be applied for thickness from 3 up to 10 mm per coat.

It is possible to apply flooring material on top of ROCKY SL 10 screed (such as ceramic, carpet, etc.) after nearly 48 hours from curing the product (depending on the thickness, the supports humidity and weather conditions).

Curing

Curing of the completed floor shall be carried out using a combination of damp hessian and polythene sheeting for a period of no less than 2 days.

Cleaning

The product is self-leveling and requires minimal finishing or troweling operation. Clean tools and equipment with water before the material hardens.

Rocky SL 10

Recommendations

Do not apply if the temperature is below +5°C

During summer season or temperature higher than +35°C, working area should be covered to prevent the direct sun effects. Keep equipment cool and use cool water

Ground floor slabs on sloping gradient must incorporate a damp-proof membrane in the sub-floor

It is advisable to mix with cool water (temperature around +20°C)

Protect the freshly applied ROCKY SL 10 from direct sunlight and/or strong drying wind

ROCKY SL 10 should not be applied over asphalt, weaker friable concrete, PVC tiles, or sheet substrates

ROCKY SL 10 should be cured for two days by covering with wet Hessian cloth and polythene sheet

Surface Preparation

The surface of the concrete to be prepared shall be sound, clean and uncontaminated. This preparation shall be such as to leave a sound exposed concrete surface free from dust, loose particles and any deleterious matter. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Excess laitance deposits are best removed by light mechanical scrubbing, grinding or grit/captive blasting followed by vacuum cleaning to remove dust debris.

All cracks and imperfections shall be repaired using ROCKY SUPERIOR FINISH 3-6, a cementitious fairing coat.

New concrete floors should be allowed to cure for at least 28 days before applying the primer

Coverage

- ROCKY SL 10 is packed in 25 kg of bags.
- Consumption: 2.0 kg/m² per millimeter of thickness.

Rocky SL 10

Shelf Life & Storage

Keep the product in a dry covered place into original well closed packaging.

Shelf life is 6 months from date of production if stored properly.

Health & Safety

ROCKY SL 10 can be harmful to skin as it contains cement powders which may releases alkalis when mixed with water.

During application, wear appropriate protective clothing, goggles, gloves and respiratory equipment if necessary.

In case of contact with skin, rinse with water and again wash thoroughly with soap and water. In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly.

If ingested, obtain medical attention immediately.

Important Note

The information in this Technical Data Sheet is based on Rocky-SCM Canada's experience. Rocky-SCM does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Rocky-SCM Data Sheets are updates on regular basis. It is the user's responsibility to obtain the latest version.